

FIBRAN_{geo} R-560-KO

Stonewool Insulation Roll with stitching wire

Technical Data Sheet / June 2022



Description

FIBRAN_{geo} R-560-KO stonewool technical insulation roll is a natural inorganic fibrous product that is industrially produced from molten rock spun into fibres, in accordance with European Standard EN 14303 (MW – Factory made Mineral Wool Insulation products).

Applications

Rolls designed for thermal insulation, fire resistance and sound insulation applications in building equipment and industrial facilities.

- Ductwork
- Valves, special curved items, flanges
- Exhaustion pipes, Hot/Cold air pipes, HVAC systems, steel chimneys
- Tank walls/roofs (cylindrical/flat)
- Boilers, Containers, Ovens, Electrostatic smoke filters
- Refinery columns
- Heat exchanger / silencer equipment
- Max. Service Temperature 650 °C

Packaging

| Thickness [mm] | Width [mm] | Length [mm] | Quantity/Roll [m ² /Roll] | Weight/Roll [kg/Roll] |
|----------------|------------|-------------|--------------------------------------|-----------------------|
| 30 | 1000 | 7200 | 7,20 | 14,04 |
| 40 | 1000 | 7200 | 7,20 | 18,72 |
| 50 | 1000 | 7200 | 7,20 | 23,40 |
| 60 | 1000 | 4800 | 4,80 | 18,72 |
| 70 | 1000 | 4800 | 4,80 | 21,84 |
| 80 | 1000 | 4800 | 4,80 | 24,96 |
| 90 | 1000 | 2400 | 2,40 | 14,04 |
| 100 | 1000 | 2400 | 2,40 | 15,60 |
| 120 | 1000 | 2400 | 2,40 | 18,72 |



Advantages

- Excellent thermal insulation
- Non-combustible material with excellent fire resistance
- Excellent sound absorption and sound reduction
- Open hive structure material with very low water vapour diffusion resistance that enhances the building element's breathability
- Excellent dimensional stability and durability
- Water repellent and non-hygroscopic
- Easy to handle, cut and install
- Natural, inorganic, odourless, chemically inert
- Recyclable, friendly to the environment and to the end user

FIBRAN^{geo} R-560-KO

Stonewool Insulation Roll with stitching wire

Technical Data Sheet / June 2022

Technical characteristics

Designation Code:

MW (Mineral Wool) - EN 14303 - T2 - ST(+/250)650 - WS1 - AW1 - CL10 - F10 - PH10,5

| Technical Characteristics | Symbol EN 14303 | Unit | Value | EN Standard |
|---|--------------------|-------------------|--|----------------------------|
| Declared thermal conductivity at 10°C | λ_D | W/(mK) | 0,035 | EN 12667 EN 13787 |
| Maximum Service Temperature | ST(+/250) | °C | 650 | EN 14706 |
| Nominal thickness | d_N | mm | 30 - 120 | EN 823 |
| Fire classification | - | Class | A1 (Non-combustible) | EN 13501-1 |
| Melting temperature | - | °C | >1000 | DIN 4102-17 |
| Specific heat capacity | c | kJ/kg*K | 1,03 | ISO 10456 |
| Thickness tolerance | T | Class | T2, (-5%, +15%) | EN 14303 |
| Short term water absorption for 24 hours | WS | kg/m ² | <1 | EN 1609 |
| Content in water-dissolved chlorine, fluorine ions and PH value | CL, F, PH | mg/kg | <10 AS-quality for use over stainless steel. PH-value neutral to slightly alcaline | EN 13468 |
| Weighted sound absorption coefficient on boards with thickness 50mm, α_w | AW | - | 1 (Class A) | EN ISO 11654 EN ISO 354 |
| Density, ρ | - | kg/m ³ | 65 | EN 1602 |

Declared thermal conductivity λ_D

| Mean Temperature | θ_M | °C | 50 | 100 | 150 | 200 | 250 | 300 | 350 | 400 | 500 | 600 | 650 | EN 14303 |
|-------------------------------|-----------------|------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|----------------------|
| Declared Thermal Conductivity | $\lambda_{N,P}$ | W/mK | 0,039 | 0,046 | 0,054 | 0,063 | 0,075 | 0,087 | 0,101 | 0,116 | 0,151 | 0,193 | 0,221 | EN 12667 EN 13787 |



FIBRAN S.A
6th km Thessaloniki - Oreokastro Rd.
P.O. Box 40306, A.C. 564 10
Thessaloniki, Greece
Tel. +30 2310 682 425. 692 700
Fax. +30 2310 683 131

info@fibran.gr
www.fibran.gr

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavour to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to the material's use.