


# FIBRANgeo CORE BL-40c

## A Multipurpose Slab for laminated core of sandwich panels

Technical Data Sheet / June 2022



0751



## Description

**FIBRANgeo CORE BL-40c** is produced from molten mineral rock, initially fused in an electric furnace at more than 1500°C and then spun into fibres. The loose stonewool fibres, with the addition of adhesive resin, oil and special compounds that provide water repellency, become cohesive, elastic, non-hygroscopic and water-repellent. Fibres are formed in boards and cut to size as required by application. Products are finally shrink-wrapped in PE film and packed on pallets.

Stonewool is a natural inorganic fibrous material, widely recognized for its thermal and sound insulating properties, as well as its excellent performance in terms of fire protection. Products are certified according to the European Standard EN 13162 (MW - Mineral Wool insulation products).

## Delivery Programme

**FIBRANgeo CORE BL-40c** slab dimensions are regularly produced upon the specification of the customer. However the format and the dimension tolerances can be respected only within the technical capability of the **FIBRANgeo** production line, that are specified below:

- **Thickness range:** 20 - 300 mm
- **Length:** 2000 mm
- **Width:** 500 – 1250 mm

*Packaging and palletizing upon customer specifications.*

## Application

**FIBRANgeo CORE BL-40c** is a light weight board dedicated for the core of sandwich panels. During the application, boards are being cut to lamella, that is reverted for 90 degrees and after inserted into the core of sandwich panel. The panel core is glued to metal coils with polyurethane glue.

**FIBRANgeo CORE BL-40c** is designed for the laminated core of the wall sandwich panels with low level of mechanical stress or for acoustic wall panels. The rotation of lamella before application changes the fibre orientation to vertical and therefore maximizes mechanical performance of the sandwich core.

**FIBRANgeo CORE BL-40c** basic mechanical and thermal properties in this document are being declared for lamella application.



## Advantages

- Excellent thermal insulation
- Non-combustible material with excellent fire resistance
- Excellent sound absorption and sound reduction
- Optimized for high Mechanical and Thermal stress
- Excellent dimensional stability and durability
- Water repellent and non-hygroscopic
- Easy to handle, cut and install
- Natural, inorganic, odourless, chemically inert (practically neutral pH)
- Recyclable, friendly to the environment and to the end user

# FIBRAN<sub>geo</sub> CORE BL-40c

## A Multipurpose Slab for laminated core of sandwich panels

Technical Data Sheet / June 2022

### Technical characteristics

Designation Code:

**MW (Mineral Wool) - EN 13162 – T5 – WS – WL(P) – MU1**

Technical Characteristics	Symbol EN 13162	Unit	Value	EN Standard
Declared thermal conductivity at 10°C	$\lambda_D$	W/(mK)	0,035	EN 13162 EN 12667 EN 12939
Nominal thickness	$d_N$	mm	20-300	EN 823
Fire classification	-	Class	A1 (Non-combustible)	EN 13501-1
Calorific value	-	MJ/kg	$\leq 2$	EN 13501
Thickness tolerance	T	Class	T5 ( $<100\text{mm}$ : -1 mm , +3 mm) ( $\geq 100\text{mm}$ : -1% , +3 mm)	EN 12431
Short term water absorption for 24 hours	WS	kg/m <sup>2</sup>	$<1$	EN 1609
Long term water absorption for 28 days	WL(P)	kg/m <sup>2</sup>	$<3$	EN 12087
Water vapor diffusion resistance factor, $\mu$	MU	-	1	EN 12086

Modulus values available upon request

### Thermal resistance R

<b>Nominal thickness</b>	$d_N$	mm	20	30	40	50	60	80	100	120	140	160	180	200	250	EN 823
<b>Declared thermal resistance</b>	$R_D$	m <sup>2</sup> K/W	0,55	0,85	1,10	1,40	1,70	2,25	2,85	3,40	4,00	4,55	5,10	5,70	7,10	EN 13162

Characteristics of lamella	Symbol	Unit	Value	EN Standard
Thermal conductivity	$\lambda$	W/(mK)	0,039	EN 13162
Compressive strength	CS	kPa	$> 40$	EN 826
Tensile strength	TR	kPa	$> 60$	EN 1607
Shear strength	SS	kPa	$> 30$	EN 12090



#### FIBRAN S.A

6<sup>th</sup> km Thessaloniki - Oreokastro Rd.

P.O. Box 40306, A.C. 564 10

Thessaloniki, Greece

Tel. +30 2310 682 425

Fax. +30 2310 683 131

info@fibran.gr

www.fibran.gr

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavour to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to the material's use.