

FIBRANgyps NEXT COAT

Description

Finishing powder to be mixed with water, based on selected inerts, hydraulic binder and special additives which give the product remarkable adhesion and elasticity. Grey color.

Use

- Glue of mineral wool panels for rendered facade type biosoluble stone wool FIBRANgeo BP ETICS
- Smooth plaster of external walls with FIBRANgyps NEXT BOARD for smooth finishes.

■ Fire reaction	A1 Class
■ Weight	1350 kg/m ³
■ Finishing	2-3 mm each coat
■ Theoretical consumption as finishing	4-6 kg/m ²
■ Working time	nearly 4 hours
■ Compression strenght after 28 d	category CS IV
■ Type of fracture	A – high flessness
■ Water vapour permeability factor	$\mu = 15$
■ Water absorption	W ₁
■ Thermal conductivity	$\lambda = 0,42$ W/mK
■ Packaging	supplied in bags on pallets with stretch

Store in a cool, dry, ventilated area. Mantein undamaged packaging. Use within the expiry date printed on the bag. Avoid sudden changes of temperature during the setting phase. Do not use FIBRANgyps NEXT COAT temperatures below + 5 ° C and above + 30 ° C.

Description	Code.	Pack.	kg /pack.	Pack. /pallet	kg /pallet
Smoothing and adhesive for exterior finish and insulation	GERASNEXT-25-R	Bag	25	60	1500

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this document is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavor to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use. For more information visit the website www.fibran.it or contact the Technical Department.

12/02/2015 – rev. 2