

FIBRANskin VENT

Flexible sheets for water proofing

Technical Data Sheet / December 2023



Material

HDPE and aluminium composite



Applications

FIBRANskin VENT membrane is used as vapour control layer underlay, flexible sheet for waterproofing for walls and roofs, produced according to EN 13859-1:2010 & EN 13859-2:2010.

It is installed over the thermal insulation layer (cold side side). Single-side **FIBRANTape ACRYL** or double-sided **FIBRANTape 2-SEAL** or **FIBRANTape BUTYL 2-sided** can be used for its application.

FIBRANskin VENT is suitable for roofs and walls (especially ventilated facades).

Technical characteristics

Property	Method	Units	Nominal Value	Minimum	Maximum
Functionality: Water vapour transmission , water tightness, weather durability, fire class					
Water vapour transmission (Sd)	EN ISO 12572	m	0,03	0,015	0,05
Temperature resistance	-	°C	-	-40	+100
Flexibility at low temperature	EN 1109	°C	-	-	-40
Water tightness	EN 1928 (A)	class	W1	-	-
Water column	EN 20811	m	2	-	-
Reaction to fire	EN ISO 11925-2	euroclass	E (*)	-	-

(*): on mineral wool and wood

FIBRANskin VENT

Flexible sheets for water proofing

Technical Data Sheet / December 2023

Physical and mechanical properties					
Mass per unit area	EN 1849-2	g/m ²	82	77	87
Maximum tensile force (MD)	EN 12311-1	N/50mm	245	220	270
Elongation at max. tensile force (MD)	EN 12311-1	%	10,5	9	12
Maximum tensile force (XD)	EN 12311-1	N/50mm	210	185	235
Elongation at max. tensile force (XD)	EN 12311-1	%	15	12,5	17,5
Resistance to tearing MD (nail shank)	EN 12310-1	N	90	70	110
Resistance to tearing XD (nail shank)	EN 12310-1	N	80	65	100
Properties after ageing					
Artificial ageing by UV and heat:	EN 1297 & EN 1296	residual value			
Water tightness	EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)	EN 12311-1	%	90	-	-
MD elongation at max. tensile force	EN 12311-1	%	85	-	-
Maximum tensile force (XD)	EN 12311-1	%	90	-	-
XD elongation at max. tensile force	EN 12311-1	%	80	-	-
Additional properties					
Length	EN 1848-2	deviation in %	0	0	-
Width	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm / 10m	-	-	30
Dimensional stability (MD & XD)	EN 1107-2	%	-	-	1
Resistance to penetration of air	EN 12114	m ³ /(m ² h 50Pa)	-	-	0,1



FIBRAN S.A

6th km Thessaloniki - Oreokastro Rd.
 P.O. Box 40306, A.C. 564 10
 Thessaloniki, Greece
 Tel. +30 2310 682 425. 692 700
 Fax. +30 2310 683 131

info@fibran.gr
 www.fibran.gr

Some test methods are modified according to the EN 13859-2:2014 and/or according to the FIBRAN ISO 9001:2008 certified quality system (for details please contact your regional FIBRAN representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, FIBRAN makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.